

20P/250 Erbium/Ytterbium-Doped LMA Double Clad PM Fiber



Coherent | Nufern's proprietary rare earth doping technology is used to deliver Er/Yb co-doped fibers with industry leading performance and reliability. This fiber feature a 20 micron diameter core and a 250 micron diameter cladding with a 0.09 NA. The fiber design has been finely optimized to deliver the best performance. PLMA-EYDF-20P/250-XPB is optimized to achieve tens of Watts of output power with high efficiency and suppressed 1 μ m parasitic ASE, offering unmatched stability. The large core of the fiber allows for shorter fiber lengths in amplifier and laser systems to reduce the impact of non-linear effects. The fiber utilizes the latest fiber design and NuCOAT-FA coating technology to ensure excellent preservation of beam quality and extended operating light at the high power levels demanded by today's industrial fiber laser applications.

Typical Applications

- Laser and amplifiers
- Military and commercial LIDAR
- High peak power, pulsed fiber amplifiers

Features & Benefits

- Optimized XPH design — High efficiency and low parasitic 1 μ m ASE
- Large core — Enables shorter fiber length for high-power pulsed amplifiers
- Double clad design — High power performance and high power conversion efficiency
- NuCOAT-FA fluoroacrylate coating — Greater fiber durability in extreme operating and storage conditions
- All fiber proof tested to > 100 kpsi — Critical for ensuring long term reliability when coiling

Optical Specifications

Operating Wavelength	1530 – 1625 nm
Core NA	0.090 \pm 0.010
First Cladding NA (5%)	\geq 0.46
Cladding Attenuation	\leq 30.0 dB/km @ 1095 nm
Cladding Absorption	3.70 \pm 0.60 dB/m at 915 nm
Core Absorption	90.0 \pm 20.0 dB/m near 1535 nm
Birefringence	nominal 1.5×10^{-4}

PLMA-EYDF-20P/250-XPB

Geometrical & Mechanical Specifications

Cladding Diameter	250.0 \pm 5.0 μ m
Core Diameter	20.0 \pm 2.0 μ m
Coating Diameter	350.0 \pm 10.0 μ m
Core/Clad Offset	\leq 2.50 μ m
Clad Non-Circularity	\leq 2.0 %
Coating Material	Low Index Acrylate
Proof test Level	\geq 100 kpsi (0.7 GN/m ²)

Matched passive delivery fiber PLMA-GDF-20/250-09M



7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • E-mail info@nufern.com • www.nufern.com • Nufern products are manufactured under an ISO 9001:2008 certified quality management system.

Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Nufern can assist with your requirements.

