

# 30/250 Ytterbium-Doped LMA Double Clad Fibers

Nufern's 30/250 Ytterbium-doped double clad Fiber is specifically designed for short pulse amplification where fiber length is a critical design factor because of very high peak powers. The high absorption enables very short fiber amplifier lengths without sacrificing efficiency. Short pulse fiber amplifiers can be considered low-costreplacements for Nd:YAG lasers used in materials processing, LIDAR and range finding applications. This 30/250 Large Mode Area fiber is available in both a standard and a PANDA-style PM format. Nufern also offers alternate versions of these fibers with higher Yb dopant concentration.

## **Typical Applications**

### **Features & Benefits**

- Short pulse fiber amplifiers & lasers •
- Materials processing
- LIDAR
- · Range finding
- CW fiber amplifiers and lasers
- NuCOAT™ fluoroacrylate coating Greater fiber durability in extreme environmental operating & storage conditions
- LMA core design and short amplifier length Useful for generating high peak powers
- "Few" moded core design Easy to maintain single mode LP01 beam through fiber & components
- PANDA-style stress structure for increased birefringence Superior optical performance and uniformity
- All fiber proof tested to > 100 kpsi Critical for ensuring long term reliability when coiling

### **Optical Specifications**

# Operating Wavelength Core NA First Cladding NA (5%) Cladding Attenuation Cladding Absorption

Birefringence

PLMA-YDF-30/250-VIII

LMA-YDF-30/250-VIII

1060 - 1115 nm 1060 - 1115 nm  $0.060 \pm 0.010$   $0.060 \pm 0.010$  ≥ 0.46 ≥ 0.46 ≤ 15.0 dB/km @ 1095 nm N/A

 $2.00 \pm 0.30$  dB/m at 915 nm 6.00 dB/m near 975 nm  $6.10 \pm 0.30$  dB/m at 915 nm

# Geometrical & Mechanical Specifications

Cladding Diameter
Cladding Diameter (flat-to-flat
Core Diameter
Coating Diameter
First Cladding Materia
Prooftest Leve

 $250.0 \pm 8.0 \,\mu \text{m}$  N/A

N/A  $250.0 \pm 8.0 \ \mu m$   $30.0 \pm 2.5 \ \mu m$   $30.0 \pm 2.5 \ \mu m$   $395.0 \pm 15.0 \ \mu m$   $395.0 \pm 15.0 \ \mu m$ Low Index Polymer Low Index Polymer ≥ 100 kpsi (0.7 GN/m²) ≥ 100 kpsi (0.7 GN/m²)





