

# Polarization Maintaining 1300 nm Telecommunication Fibers

Nufern's Polarization Maintaining Telco fibers are designed for today's most advanced networks. Optimized for use at 1310 nm, these fibers are used in all PM applications for data and telecom. Nufern has applied its unique manufacturing facility and capabilities to this product area and has established leading optical, mechanical and geometrical tolerances. The bend insensitive versions of our fibers offer lowest bend loss and extinction ratios at small bend diameters enabling our customers to reduce package sizes. Available in either 250 or 400 micron coating diameters and prooftested to 200 kpsi, Nufern's PM fibers will meet the demands of all current and future applications.

## **Typical Applications**

- · Pump and source pigtails
- PM patchcords
- · Polarization sensitive devices

### **Features & Benefits**

- Tight specifications Highly deterministic results, highest product yield
- High fatigue failure resistance Longest service life
- Bend insensitive Survives application in tight geometries (B version)
- All fiber proof tested to > 200 kpsi Critical for ensuring long term reliability

## **Optical Specifications**

Operating Wavelength Core NA Mode Field Diameter Maximum Bend Loss

Cutoff Core Attenuation Beat Length Normalized Cross Talk

Bending Cross Talk

# PM1300-XP

1270 - 1625 nm 0.120 N/A

≤ 4 mm @ 1300 nm

1300 nm

9.3 ± 0.5 µm @ 1300 nm  $1210 \pm 60 \text{ nm}$ ≤ 1.0 dB/km @ 1300 nm ≤ - 40.0 dB at 4 m @ 1300 ≤ - 30.0 dB at 100 m @

N/A

# PM1300B-XP

1270 - 1625 nm 0.120 9.3 ± 0.5 um @ 1300 nm 0.5 dB at 1300 nm, 25 mm OD. 10 turns  $1210 \pm 60 \text{ nm}$ ≤ 1.0 dB/km @ 1300 nm

≤ 4 mm @ 1300 nm ≤ - 40.0 dB at 4 m @ 1300 nm ≤ - 30.0 dB at 100 m @

1300 nm -30 dB at 1300 nm, 25 mm OD, 10 turns

# PM1300-400

1270 - 1625 nm 0.120 9.3 ± 0.5 µm @ 1300 nm

N/A

 $1210 \pm 60 \text{ nm}$ ≤ 1.0 dB/km @ 1300 nm ≤ 4 mm @ 1300 nm

≤ - 40.0 dB at 4 m @ 1300

1300 nm

≤ - 30.0 dB at 100 m @ N/A

## PM1300B-400

1270 - 1625 nm 0.120

9.3 ± 0.5 um @ 1300 nm 0.5 dB at 1300 nm, 25 mm

OD, 10 turns  $1210 \pm 60 \text{ nm}$ 

≤ 1.0 dB/km @ 1300 nm

≤ 4 mm @ 1300 nm

≤ - 40.0 dB at 4 m @ 1300

nm

≤ - 30.0 dB at 100 m @

1300 nm

-30 dB at 1300 nm, 25 mm OD, 10 turns

# Geometrical & Mechanical **Specifications**

Cladding Diameter Core Diameter Coating Diameter Coating Concentricity Core/Clad Offset Coating Material Operating Temperature Range Prooftest Level

 $125.0 \pm 1.0 \, \mu m$ 8.0 µm  $245.0 \pm 15.0 \, \mu m$ < 5.0 um ≤ 0.50 µm UV Cured, Dual Acrylate

-40 to 85 °C  $\geq$  200 kpsi (1.4 GN/m<sup>2</sup>)

 $125.0 \pm 1.0 \, \mu m$ 8.0 µm  $245.0 \pm 15.0 \, \mu m$  $< 5.0 \, um$  $\leq 0.50 \, \mu \text{m}$ UV Cured, Dual Acrylate

-40 to 85 °C ≥ 200 kpsi (1.4 GN/m²)  $125.0 \pm 1.0 \, \mu m$ 8.0 µm  $400.0 \pm 15.0 \, \mu m$ < 10.0 um  $\leq 0.50 \, \mu \text{m}$ UV Cured, Dual Acrylate

-40 to 85 °C  $\geq$  200 kpsi (1.4 GN/m<sup>2</sup>)  $125.0 \pm 1.0 \, \mu m$ 8.0 µm

 $400.0 \pm 15.0 \, \mu m$ < 10.0 um  $\leq 0.50 \, \mu \text{m}$ 

UV Cured, Dual Acrylate

-40 to 85 °C

≥ 200 kpsi (1.4 GN/m²)

Special Core Dopants: SiO2/GeO2.



