

5/130 Ytterbium-Doped Double-Clad Fiber

Nufern's general purpose Ytterbium-Doped Double-Clad Fiber is available in two-versions — PANDA-style, polarization-maintaining (PM) and non-PM. Designed specifically for CW applications around 1-15 W, these fibers are ideal for applications requiring low-cost fiber laser and amplifier source, such as laser marking, fiber amplifier pumps and IR sources for frequency doubling. These fibers' telecom-type geometrics are compatible with readily available low-cost pump diodes and fiber-based components.

Typical Applications

- · Laser marking
- Fiber amplifier pumps
- IR sources for frequency doubling

Features & Benefits

- NuCOAT™ fluoroacrylate coating Greater fiber durability in extreme environmental operating & storage conditions
- Low cost double-clad technology Enables use of high power multimode pump diodes
- Single-mode output Compatiable with standard telecom 980/1060 nm fiber-based components
- PANDA-style stress structure Linearly polarized output for frequency conversion

SM-YDF-5/130-VIII

Optical Specifications

Operating Wavelength
Core NA
First Cladding NA (5%)
Mode Field Diameter

Mode Field Diameter Cutoff

Core Attenuation
Cladding Attenuation
Cladding Absorption

Birefringence

PM-YDF-5/130-VIII

 2.5×10^{-4}

m 1060 – 1115 nm

1060 - 1115 nm 1060 - 1000 -

 $6.5 \pm 0.5 \, \mu m$ @ 1060 nm $6.5 \pm 0.5 \, \mu m$ @ 1060 nm

 $950 \pm 50 \text{ nm}$ $950 \pm 50 \text{ nm}$

 \leq 15.0 dB/km @ 1200 nm \leq 15.0 dB/km @ 1095 nm \leq 15.0 dB/km @ 1095 nm \leq 15.0 dB/km @ 1095 nm 0.60 ± 0.10 dB/m at 915 nm 1.80 dB/m near 975 nm 1.65 dB/m near 975 nm

N/A

Geometrical & Mechanical Specifications

Cladding Diameter
Cladding Diameter (flat-to-flat)
Core Diameter
Coating Diameter
Coating Concentricity
Core/Clad Offset
Prooftest Level

 $130.0 \pm 1.0 \, \mu \text{m}$ N/A

N/A $130.0 \pm 1.5 \, \mu m$ $5.0 \, \mu m$ $5.0 \, \mu m$ $245.0 \pm 10.0 \, \mu m$ $< 5.0 \, \mu m$ $< 5.0 \, \mu m$ $< 5.0 \, \mu m$ $≤ 1.00 \, \mu m$

 \geq 100 kpsi (0.7 GN/m²) \geq 100 kpsi (0.7 GN/m²)



The passive version of each fiber is also available - see PM-GDF-5/130 and SM-GDF-5/130



