# **C-Band Erbium Doped Fibers**



Nufern's high performance C-Band Erbium-Doped 980-HP Fibers are designed for use in single and multi-channel C-band amplifiers and ASE sources. The  $80 \, \mu m$  version is suitable for small form-factor amplifiers and metro amps. The "HI" version is designed to achieve the highest possible optical efficiencies in applications where available pump power is limited. All Nufern erbium-doped fibers are fabricated with a proprietary technology and have highly consistent and reproducible spectroscopy

### **Typical Applications**

- Single and multi-channel C-band amplifiers
- ASE sources
- Small form factor amps
- Metro amps

#### **Features & Benefits**

- Highly consistent and reproducible spectroscopy high manufacturing yields when matching to a GFF
- Excellent core concentricity low splice loss to single-mode fibers

EDFC-980-HP-80

High aluminum concentration — inherent gain flatness

### **Optical Specifications**

Operating Wavelength Core NA Mode Field Diameter

Cutoff Core Attenuation Core Absorption

#### EDFC-980-HP

1530 – 1565 nm

1530 – 1565 nm 1530 – 0.230 0.230

5.8 ± 0.5 µm @ 1550 nm 5.8 ± 0.5 µm @ 1550 nm

920 ± 50 nm 920 ± 50 nm

 $\leq$  15.0 dB/km @ 1200 nm  $\leq$  15.0 dB/km @ 1200 nm 6.00  $\pm$  1.00 dB/m near 1530 6.50  $\pm$  3.50 dB/m at 980 nm 6.00  $\pm$  1.00 dB/m near 1530

 $6.50 \pm 3.50 \, dB/m \, near \, 980 \, nm$ 

nm

## Geometrical & Mechanical Specifications

Cladding Diameter
Core Diameter
Coating Diameter
Coating Concentricity
Core/Clad Offset
Coating Material
Operating Temperature Range

Prooftest Level

 $125.0 \pm 1.0 \, \mu m$   $80.0 \pm 1.0 \, \mu m$   $3.2 \, \mu m$   $3.2 \, \mu m$   $245.0 \pm 10.0 \, \mu m$   $< 5.0 \, \mu m$   $< 5.0 \, \mu m$   $≤ 0.30 \, \mu m$  A crylate A crylate -40 to 85 °C  $+0.0 \, \mu m$   $+0.0 \, \mu m$  +0.0

 $\geq$  200 kpsi (1.4 GN/m<sup>2</sup>)  $\geq$  200 kpsi (1.4 GN/m<sup>2</sup>)



