



EyeSafe 25 Micron Core Holmium-Doped LMA Double Clad Fiber

True LMA fiber featuring a unique low NA (< 0.1) high concentration Ho-doped core design. The Ho-doped fiber can be pumped by a Tm-doped fiber laser at ~ 1950 -nm and can achieve 60% efficiency. The high NA (0.46) large pump cladding waveguide allows for efficient coupling of high pump powers. The large core diameter (25 μm) maintains a large mode field diameter and short device length, thereby minimizing non-linear effects such as SBS and SRS.

Typical Applications

- High power CW and pulsed
- EyeSafe (~ 2 μm) lasers and amplifiers
- Military and commercial LIDAR
- ~ 2 μm output TEM₀₀ fiber lasers for pumping solid state crystal lasers

Features & Benefits

- Unique low NA Ho-doped core design — Robust single-mode beam quality
- NuCOAT™ fluoroacrylate coating — Greater fiber durability in extreme environmental operating & storage conditions
- High pump absorption — Short fiber length, efficient lasing in the ~ 2 μm window

Optical Specifications

Operating Wavelength	2100 – 2200 nm
Core NA	0.080 ± 0.010
First Cladding NA (5%)	≥ 0.46
Cladding Attenuation	≤ 15.0 dB/km @ 810 nm
Cladding Absorption	0.30 ± 0.20 dB/m at 1150 nm

LMA-HDF-25/250

Geometrical & Mechanical Specifications

Cladding Diameter (flat-to-flat)	250.0 ± 8.0 μm
Core Diameter	25.0 ± 2.0 μm
Coating Diameter	395.0 ± 15.0 μm
Core/Clad Offset	≤ 2.00 μm
Proof test Level	≥ 100 kpsi (0.7 GN/m ²)



7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 E-mail info @ nufern.com • www.nufern.com •
Nufern products are manufactured under an ISO 9001:2008 certified quality management system.



Standard specifications and design parameters are listed above. Specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Nufern can assist with your requirements.

NU0146- 11/07/2013