



1407024

MM-GTF-34/460/530, Matched Passive Triple Clad Optical Fiber



www.nufern.com

Parameters	Min	Max	Nom	Unit	Compliance
Core Attenuation at 1200 nm	0	15		dB/km	Measured
Core NA	0.09	0.11	0.1		Measured
First Clad NA (50%)	0.2	0.24	0.22		Measured
Second Clad NA (5%)	0.46				Design
Core Diameter	31.5	36.5	34	μm	Measured
First Clad Diameter	450	470	460	μm	Measured
Second Clad Diameter	520	540	530	μm	Measured
Core/Clad Offset	0	3		μm	Measured
Coating Diameter	635	665	650	μm	Measured
Proof test Level	100	120		kpsi	Measured
Operating Wavelength	1015	1600		nm	Design

Comments

Coating Requirements: Low index polymer NuCOAT-FA-HP.

